

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 3660-1 (1999): Methods of Test for Natural Rubber, Part 1: Determination of Dirt [PCD 13: Rubber and Rubber Products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS 3660 (Part 1) : 1999

भारतीय मानक
प्राकृतिक रबड़ की परीक्षण विधियाँ

REAFFIRMED

21 2003

भाग 1 मूल ज्ञात करना

[एन आर : 1]

(~~द्वितीय~~ पुनरीक्षण)

Indian Standard

METHODS OF TEST FOR NATURAL RUBBER

PART 1 DETERMINATION OF DIRT

[NR : 1]

(*Third Revision*)

ICS 83.060; 19.020

© BIS 1999

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

June 1999

Price Group 2

FOREWORD

This Indian Standard (Third Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Rubber Sectional Committee had been approved by the Petroleum, Coal and Related Products Division Council.

Methods of test for natural rubber had been originally covered in the following four parts:

IS 3660 (Part I) : 1972 Determination of dirt, volatile matter, ash, total copper, manganese, rubber hydrocarbon, viscosity (shearing disk viscometer), and mixing and vulcanizing of rubber in a standard compound [subsequently designated as IS 3660 (Part 51) : 1972].

IS 3660 (Part II) : 1968 Determination of solvent extract and nitrogen content [subsequently designated as IS 3660 (Part 52) : 1968].

IS 3660 (Part III) : 1971 Plasticity and plasticity retention index [subsequently withdrawn with the publication of Parts 11 and 12 of IS 3660 in 1989].

IS 3660 (Part IV) : 1979 Determination of colour, accelerated storage-hardening test and vulcanization characteristics (MOD test) [subsequently designated as IS 3660 (Part 54) : 1979].

While reviewing various test methods for natural rubber, the Committee decided to align them with the corresponding International Standards. Unification of test methods for natural and synthetic rubber has not been considered necessary. However, in revising test methods for natural rubber, the Committee had decided to revise and split the standards into further parts and publish test methods for individual characteristics under natural rubber (NR) series. For proper referencing of the original test methods and the new methods revised/under revision, a table showing correspondence of the various methods of test covered in the previous 4 parts of IS 3660, namely (Part I, II, III and IV) with the presently split parts have been given in Annex A. In order to facilitate cross reference, it has been decided to retain the original discrete NR series numbers assigned to various test methods in original IS 3660 (Part I, II, III and IV) in the revised part of IS 3660.

In the preparation of this standard, assistance has been derived from ISO 249 : 1995 (E) 'Rubber, raw natural — Determination of dirt content', published by the International Organization for Standardization (ISO).

In this revision toyl mercaptan has been included as an additional peptizing agent and xylyl mercaptan has been deleted. Method for determination of dirt content has been elaborated.

In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS 2 : 1960 'Rules for rounding off numerical values (revised)'.
(revised)

*Indian Standard***METHODS OF TEST FOR NATURAL RUBBER****PART 1 DETERMINATION OF DIRT**

[NR : 1]

*(Third Revision)***1 SCOPE**

This standard (Part 1) prescribes the method of test for the determination of dirt content of raw natural rubber.

2 NORMATIVE REFERENCES

The following Indian Standards contain provisions which through reference in this text, constitute provisions of this standard. At the time of publication the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below:

| <i>IS No.</i> | <i>Title</i> |
|---------------------------|-----------------------------------------------------------------------------------------------|
| 460 (Part 1) : 1985 | Test sieves: Part 1 Wire cloth test sieves (<i>third revision</i>) |
| 1381 (Part 2) : 1977 | Boiling flasks : Part 2 Flasks with conical ground socket (<i>first revision</i>) |
| 2480 (Part 1) : 1983 | General purpose glass thermometers : Part 1 Solid stem thermometers (<i>first revision</i>) |
| 5599 : 1970 | Methods of sampling of raw rubber |

3 APPARATUS**3.1 Chemical/Electronic Balance****3.2 Conical Flask**

500 ml capacity [*see* IS 1381 (Part 2)].

3.3 Desiccator with Efficient Desiccant**3.4 Thermometer**

To read atleast 200°C [*see* IS 2480 (Part 1)].

3.5 Heater

For heating conical flask and its contents. Hot plates which provide uniform heating surfaces, or heater with

infra red lamp or a sand bath may be used.

3.6 Wire Sieve

Of nominal size of opening 45 micron IS Sieve [*see* IS 460 (Part 1)].

3.6.1 The wire sieve shall be mounted across the bottom surface of a stainless steel tube of internal diameter 25 mm and outer diameter 30 mm. The height of the sieve frame shall not be less than 15 mm.

3.7 Ultrasonic Equipment, for Cleaning Sieves**4 REAGENTS**

4.1 High aromatic hydrocarbon solvent known as white spirit or low aromatic hydrocarbon solvent such as turpentine or kerosene with boiling range above 150°C.

4.2 Mixed Xylenes, Boiling Range Above 140°C

4.3 Petroleum hydrocarbon solvent, such as petroleum ether with boiling range 60-80°C.

4.4 Toluene**4.5 Rubber Peptizing Agents**

4.5.1 Toyl mercaptan solution, 20 percent (*m/m*) to 40 percent (*m/m*) in high aromatic hydrocarbon solvent.

4.5.2 Copper Oleate

NOTE — *Preparation of copper oleate* — Dissolve 6.58 g of sodium hydroxide in about 65 ml water and 46.38 g oleic acid with stirring. Filter the solution through Whatman filter paper (No. 41). Wash the precipitate 2 or 3 times with distilled water so as to remove the excess sodium hydroxide. Take out the precipitate in clean beaker and dissolve it in about 500 ml water by heating. To this add concentrated solution of copper sulphate, prepared by dissolving 25 g of copper sulphate in water and heat at 90 to 95°C. Stir the mixture for one hour. Separate the top layer of copper oleate, wash with water and purify in a separating funnel using diethyl ether as solvent. Keep the copper oleate as 25 percent solution in pure mineral turpentine or benzene.

4.5.3 Other fully soluble rubber peptizing agent.

5 PROCEDURE

5.1 To the conical flask add around 200 ml rubber solvent and 1 ml of the rubber peptizing agent solution.

5.2 Weigh 10 g of rubber from the test portion, as specified in IS 5599 to the nearest 0.1 g. Cut into strips and place in the conical flask.

5.3 Heat the flask and its contents at 125 to 130°C until a smooth solution is obtained or stand for several hours at room temperature in closed condition before heating to 125 to 130°C.

5.4 Shake the flask occasionally during the standing and heating periods by hand. Boiling or overheating of the rubber solution may result in the formation of a gel like substance which renders subsequent filtration difficult and may result in a higher apparent dirt content. Hence avoid apparatus and conditions which can cause local overheating.

5.5 When the rubber is completely dissolved, decant the hot solution through the sieve which has been weighed to the nearest 0.1 mg, retaining the bulk of the dirt in the flask.

5.6 Wash the dirt in the flask 3 or 4 times with 20 to 30 ml each of hot solvent and transfer completely to the sieve.

5.7 Wash the sieve twice with petroleum hydrocarbon solvent (4.3) and dry at 100°C for 30 minutes or with

solvent (4.1 and 4.2) and dry at 100°C for 1 h.

5.8 The dirt on the sieve after drying should be loose and free-flowing. If this is not so, treat the sieve with boiling toluene (4.4).

5.9 Cool the sieve and residue in a desiccator and weigh to the nearest 0.1 mg.

5.10 Carry out three determinations.

6 CARE OF SIEVES

6.1 At all stages handle the sieve carefully. Inspect it after each determination to check for damage or block of perforations with the help of a slide projector. If noticeable distortion or block of holes are seen, replace it by a new sieve.

6.2 Sieve may be stored in warm toluene to lessen build up of rubber.

7 EXPRESSION OF RESULTS

The dirt content expressed as a percentage by mass of the test portion is given by the formula:

$$\text{Dirt content, percent by mass} = \frac{M_1}{M_2} \times 100$$

where

M_1 = mass in g of the dirt, and

M_2 = mass in g of the test portion.

ANNEX A (Foreword)

TABLE SHOWING CORRESPONDENCE OF THE VARIOUS METHODS OF TEST COVERED IN THE ORIGINAL IS 3660 (Part 1) : 1972 (NOW DESIGNATED AS Part 51), IS 3660 (Part 2) : 1968 (NOW DESIGNATED AS Part 52), IS 3660 (Part 3) : 1971 (SINCE WITHDRAWN ON ITS COMPLETE REVISION), AND IS 3660 (Part 4) : 1979 (NOW DESIGNATED AS Part 54) WITH THE NEW REVISED STANDARDS

| <i>Test Method</i> | <i>IS No.</i> | <i>Original Part (Series)</i> | <i>IS No.</i> | <i>New Parts Series</i> | <i>Remarks/ Reaffirmed</i> |
|----------------------------------|---------------|-------------------------------|----------------------|-------------------------|----------------------------|
| (1) | (2) | (3) | (4) | (5) | (6) |
| <i>NR Series</i> | | | | | |
| Determination of dirt | 3660 : 1972 | Part 1 (NR : 1) | 3660 (Part 1) : 1999 | (NR : 1) | — |
| Determination of volatile matter | 3660 : 1972 | Part 1 (NR : 2) | 3660 (Part 2) : 1985 | (NR : 2) | December 1995 |
| Determination of ash | 3660 : 1972 | Part 1 (NR : 3) | 3660 (Part 3) : 1988 | (NR : 3) | January 1995 |
| Determination of total copper | 3660 : 1972 | Part 1 (NR : 4) | 3660 (Part 4) : 1988 | (NR : 4) | January 1995 |

| <i>Test Method</i> | <i>IS No.</i> | <i>Original Part (Series)</i> | <i>IS No.</i> | <i>New Parts Series</i> | <i>Remarks/ Reaffirmed</i> |
|-----------------------------------------------------------|---------------|-------------------------------|-------------------------------------------------|-------------------------|--------------------------------|
| (1) | (2) | (3) | (4) | (5) | (6) |
| Determination of manganese | 3660 : 1972 | Part 1 (NR : 5) | 3660 (Part 5) : 1989 | (NR : 5) | January 1995 |
| Determination of iron | 3660 : 1972 | Part 1 (NR : 6) | Deleted since this test is no longer being done | | |
| Determination of rubber hydrocarbon | 3660 : 1972 | Part 1 (NR : 7) | 3660 (Part 6) : 1988 | (NR : 7) | January 1995 |
| Determination of Viscosity by shearing disk viscometer | 3660 : 1972 | Part 1 (NR : 8) | 3660 (Part 7) : 1988 | (NR : 8) | January 1995 |
| Mixing and vulcanizing in a standard compound | 3660 : 1972 | Part 1 (NR : 9) | 3660 (Part 8) : 1999 | (NR : 9) | — |
| Determination of solvent extract | 3660 : 1968 | Part 2 (NR : 10) | 3660 (Part 9) : 1989 | (NR : 10) | January 1995 |
| Determination of nitrogen | 3660 : 1968 | Part 2 (NR : 11) | 3660 (Part 10) | (NR : 11) | — |
| Determination of plasticity | 3660 : 1971 | Part 3 (NR : 12) | 3660 (Part 11) : 1989 | (NR : 12) | January 1995 |
| Determination of plasticity retention index (PRI) | 3660 : 1972 | Part 3 (NR : 13) | 3660 (Part 12) : 1989 | (NR : 13) | January 1995 |
| Determination of colour | 3660 : 1979 | Part 4 (NR : 14) | 3660 (Part 13) : 1997 | (NR : 14) | — |
| Determination of storage hardening test | 3660 : 1979 | Part 4 (NR : 15) | 3660 (Part 14) | (NR : 15) | Revision still to be published |
| Determination of vulcanization characteristics (MOD test) | 3660 : 1979 | Part 4 (NR : 16) | 3660 (Part 15) | (NR : 16) | do |
| Method of preparation of test samples | 3660 : 1972 | Part 1 (Clause 3) | 5599 : 1999 | | |

NOTES

- 1 Original IS 3660 (Part I) : 1972 now redesignated as IS 3660 (Part 51) : 1972.
- 2 Original IS 3660 (Part II) : 1968 now redesignated as IS 3660 (Part 52) : 1968.
- 3 Subsequent to its complete revision, IS 3660 (Part III) : 1971 has since been withdrawn.
- 4 Original IS 3660 (Part IV) : 1979 now re-designated as IS 3660 (Part 54) : 1979.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards : Monthly Additions'.

This Indian Standard has been developed from Doc : No. PCD 14 (1610).

Amendments Issued Since Publication

| Amend No. | Date of Issue | Text Affected |
|-----------|---------------|---------------|
| | | |
| | | |
| | | |
| | | |

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones : 323 01 31, 323 94 02, 323 33 75

Telegrams: Manaksanstha
(Common to
all offices)

Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg
NEW DELHI 110002

Telephone

{ 323 76 17
323 38 41

Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola
CALCUTTA 700054

{ 337 84 99, 337 85 61
337 86 26, 337 86 62

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022

{ 60 38 43
60 20 25

Southern : C. I. T. Campus, IV Cross Road, CHENNAI 600113

{ 235 02 16, 235 04 42
235 15 19, 235 23 15

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)
MUMBAI 400093

{ 832 92 95, 832 78 58
832 78 91, 832 78 92

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR.
COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR.
KANPUR. LUCKNOW. NAGPUR. PATNA. PUNE. THIRUVANANTHAPURAM.